

# 2018 NC On-Farm Trials (Fiber Quality)

Variety	Lint	MIC	%	LEN	STR	%	%	UI	%	%	HVI	LEAF
	%		PREM			PREM	LOW		PREM	LOW		
DP 1835 B3XF	43.2	4.38	23	1.15	30.2	85	0	81.9	46	0	41-2	4
PHY 340 W3FE	42.4	4.32	38	1.14	30.4	85	0	82.6	100	0	41-2	4
DP 1646 B2XF	41.9	4.30	46	1.22	30.4	92	0	82.7	92	0	41-1	4
PHY 430 W3FE	41.4	4.38	31	1.10	30.3	85	0	82.4	77	0	41-2	4
NG 5711 B3XF	41.2	4.29	54	1.17	31.1	100	0	82.1	62	0	41-2	3
DG 3605 B2XF	40.8	4.22	62	1.22	30.5	85	0	82.6	85	0	41-1	3
NG 3522 B2XF	40.0	4.38	31	1.10	27.5	0	8	81.4	15	8	41-2	3
DG 1702 GLT	40.0	4.20	54	1.13	29.8	69	0	81.5	38	15	41-2	3
ST 5471 GLTP	39.6	4.24	46	1.15	30.4	100	0	81.9	62	0	41-2	3
ST 5020 GLT	38.8	4.39	38	1.20	32.3	100	0	83.3	92	0	41-2	4