

# 2019 NC On-Farm Trials (Fiber Quality)

Variety	Lint %	MIC	% HIGH MIC	LEN	% SHORT STAPLE	STR	UI	HVI Color	LEAF
DP 1646 B2XF	41.9	4.58	6	1.23	0	31.4	83.7	31-1	3
ST 4550 GLTP	42.6	4.74	13	1.16	0	32.3	83.6	31-2	3
DG 1702 GLT	39.7	4.42	13	1.14	6	31.2	82.1	31-1	3
ST 5471 GLTP	39.3	4.55	13	1.16	6	31.8	82.4	31-1	3
DG 3605 B2XF	41.4	4.51	6	1.24	0	31.4	83.5	31-1	3
NG 4936 B3XF	39.7	4.67	13	1.21	0	31.3	84.7	31-1	3
PHY 350 W3FE	39.6	4.64	19	1.18	0	32.4	83.7	31-2	3
PHY 340 W3FE	42.2	4.61	6	1.16	6	32.4	83.6	31-2	4
DP 1916 B3XF	42.7	4.76	19	1.16	0	33.6	83.9	31-2	3
NG 3522 B2XF	40.9	4.65	13	1.11	0	28.7	82.1	31-2	3